

下村 鋼種記号
SGF06E
SGF07E
SF20F
SF20T
SUS430F
SUS430

化学成分 (wt%)									
C	Si	Mn	P	S	Cr	Mo	Pb	Te	他
≦0.050	≦1.00	≦2.00	≦0.050	≧0.15	13.00 - 15.00	-	-	0.010 - 0.070	特殊元素添加
≦0.050	≦1.00	≦2.00	≦0.050	≧0.15	18.00 - 20.00	-	-	0.010 - 0.070	特殊元素添加
≦0.050	≦1.00	≦2.00	≦0.050	≧0.15	19.00 - 21.00	1.50 - 2.50	-	0.010 - 0.070	特殊元素添加
≦0.050	≦1.00	≦2.00	≦0.050	≧0.15	19.00 - 21.00	1.50 - 2.50	0.10 - 0.30	0.010 - 0.070	-
≦0.12	≦1.00	≦1.25	≦0.060	≧0.15	16.00 - 18.00	≦0.60	-	-	-
≦0.12	≦0.75	≦1.00	≦0.040	≧0.030	16.00 - 18.00	-	-	-	-